

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01B 7/36, C08L 27/12, C08K 9/06	A1	(11) International Publication Number: WO 95/23417 (43) International Publication Date: 31 August 1995 (31.08.95)
(21) International Application Number: PCT/US95/01941 (22) International Filing Date: 24 February 1995 (24.02.95) (30) Priority Data: 08/203,157 28 February 1994 (28.02.94) US 08/387,987 13 February 1995 (13.02.95) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: BIRMINGHAM, John, Nicholas, Jr.; 2518 Teal Road, Wilmington, DE 19805-1078 (US). HOLTZEN, Dwight, Alan; 1133 Old Baltimore Pike, Newark, DE 19702-1105 (US). HUNT, James, Francis; 9471 55th Avenue West, Mukilteo, WA 98275-4801 (US). JENKINS, Robert, Sterrett; 806 Pheasant Run, West Chester, PA 19380 (US). SPOHN, Peter, Dwight; 2020 Longcome Drive, Wilmington, DE 19810 (US). WALNOCK, James, Thomas; 2611 Lamper Lane, Wilmington, DE 19808 (US). (74) Agents: TOCKER, Edwin et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: CN, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: LASER MARKING OF FLUOROPOLYMER COMPOSITION (57) Abstract Laser marking of pigmented fluoropolymer substrates is enhanced by using titanium dioxide pigment coated with organo silane.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgystan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE**LASER MARKING OF FLUOROPOLYMER COMPOSITION**

This application is a continuation of patent application Serial No. 08/203,157, filed February 28, 1994 by the same inventors.

5 FIELD OF THE INVENTION

This invention is in the field of laser marking of fluoropolymer composition substrates.

BACKGROUND OF THE INVENTION

European Patent Application 329884/1989 discloses a method of marking
10 a cable using an intense source of ultraviolet or visible radiation, preferably a laser source. According to this method, the exposure of PTFE, FEP, and ETFE electrical insulating layers containing up to 20 wt%, preferably up to 5 wt%, of TiO₂ as photosensitive substance to the intense radiation results in a darkening where the radiation is incident. By controlling the pattern of incidence, marks
15 such as letters and numerals can be formed.

The darkening of the substrate is understood to be caused primarily by interaction between the radiation and the TiO₂ pigment. When ultraviolet (UV) radiation is used and the polymer matrix is transparent to UV as for PTFE and FEP, this interaction will be the sole contribution to darkening. In
20 some cases, the polymer itself may darken somewhat and contribute to the mark, as for ETFE.

The laser marking technique is attractive for generating identifying marks on insulated wires to be used in complex wire harnesses, such as those found in airplanes. Since the multiplicity of circuits would impose
25 unreasonable demands on color coding and on inventory, and since white is good background for marking, white is favored for such uses. Laser marking has advantages over alternative marking techniques such as hot stamping and ink printing, in that there is no potential for mechanical damage as in hot stamping, the difficulties of adhering inks to fluoropolymers are avoided, and
30 the mark is actually beneath the surface and not easily abraded away.

An important characteristic that contributes to the readability of a mark is the contrast between mark and background. Contrast numerically is the difference between reflectances of mark and background, divided by reflectance of the background, and may be expressed as a number in the range 0-1 or in
35 percent. Maximum possible numerical contrast corresponds to an absolutely black mark (zero reflectance). If the mark is not absolutely black (non-zero reflectance), then the whiteness of the background contributes with numerical contrast increasing as background reflectance approaches unity. Minimum contrast acceptable to aircraft manufacturers for ease of wire identification is

about 60% for melt-fabricated fluoropolymer insulation or jacket. While existing compositions comprising TiO₂ pigment in a fluoropolymer matrix have provided generally white appearance, such substrates sometimes yield laser marks with good contrast, but at other times relatively poor contrast. This is
5 illustrated by the photomicrographs of laser marks in Figure 6. The mark in Figure 6(b) has low contrast with respect to the background, of the order of 50% and would not meet a minimum contrast requirement of 60%. Improved contrast and uniformity of contrast are desired to facilitate identification of wires by operators during production and maintenance operations on wire
10 harnesses, for example, those used in aircraft electrical systems.

U.S. Patent 5,206,280 discloses the use of a second white pigment that does not absorb UV radiation to enhance background whiteness and thereby enhance the contrast of laser marks. No performance data are given.

SUMMARY OF THE INVENTION

15 This invention provides an improved laser-markable fluoropolymer substrate which can be formed by melt processing of a fluoropolymer composition containing TiO₂ pigment. According to the present invention, it has been discovered that TiO₂ pigment when melt compounded with a melt-fabricable fluoropolymer, while yielding a white appearance, is also
20 characterized by the presence of some agglomerates. These agglomerates are not visible to the naked eye; some can be observed in cross-sections of the melt-fabricated composition under high optical magnification, while most are only detectable under the magnifications of electron microscopy. It has been found that the substantial reduction of the population of these agglomerates
25 present in fluoropolymer substrate for laser marking is accompanied by improved marking characteristics. This has been accomplished in the present invention by using TiO₂ pigment coated with organo silane in the fluoropolymer composition from which the substrate is formed.

One embodiment of the present invention is in the process of laser
30 marking a melt-fabricated substrate comprising melt-fabricable fluoropolymer and TiO₂ pigment, the improvement comprising said TiO₂ pigment having a coating comprising organo silane.

Another embodiment is a fluoropolymer composition *per se*, comprising melt-fabricable fluoropolymer and TiO₂ coated with a coating
35 comprising organo silane.

Another aspect of the present invention is the discovery that the aforesaid composition in a form yet to be melt fabricated into a finished article has improved fabricability manifested, e.g., by the ability to incorporate higher TiO₂ loadings into the composition uniformly. This improvement is also seen

by improved yield due to reduced frequency of defects in finished articles. This aspect of the invention can be defined as an improvement in the process of melt extruding the fluoropolymer/TiO₂ composition, the improvement comprising conducting the melt extrusion with the pigment coated with organo silane.

5 Another embodiment is wire insulation or cable jacket fabricated from the composition of the invention.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1(a) and (b). Photomicrographs at 70X magnification of FEP resin extrudates containing TiO₂ pigments, Fig. 1(a) without silane coating, showing scattered dark specks identified as pigment agglomerates, and Fig. 1(b) with organo silane coating, showing the essential absence of dark specks (agglomerates). The same improvement is shown in Figures 2 (a) and (b) to 5 (a) and (b) for TiO₂ pigmented compositions with other fluoropolymers.

Fig. 2 (a) and (b). Photomicrographs of PFA resin extrudate containing TiO₂ pigments, Fig. 2 (a) without silane coating and Fig. 2 (b) with organo silane coating.

Fig. 3 (a) and (b). Photomicrographs of ECTFE resin extrudate containing TiO₂ pigments, Fig. 3 (a) without silane coating and Fig. 3 (b) with organo silane coating.

Fig. 4 (a) and (b). Photomicrographs of PVDF resin extrudate containing TiO₂ pigments, Fig. 4 (a) without silane coating and Fig. 4 (b) with organo silane coating.

Fig. 5 (a) and (b). Photomicrographs of ETFE resin extrudate containing TiO₂ pigments, Fig. 5 (a) without silane coating and Fig. 5 (b) with organo silane coating.

Fig. 6 (a) and (b). Photomicrographs of laser marks on ETFE wire insulation containing TiO₂ pigment showing, Fig. 6 (a) good contrast and Fig. 6 (b) low contrast.

Fig. 7. Photomicrograph of ETFE resin extrudate containing TiO₂ pigment with silane/siloxane coating.

Fig. 8. Photomicrograph of ETFE resin extrudate containing TiO₂ pigment with octadecyl silane coating.

Fig. 9. Photomicrograph of ETFE resin extrudate containing TiO₂ pigment with methyl silane coating.

Fig. 10. Photomicrograph of ETFE resin extrudate containing TiO₂ pigment with hexyl silane coating.

Fig. 11. Photomicrograph of ETFE resin extrudate containing TiO₂ pigment with fluoroalkyl silane coating.

DETAILED DESCRIPTION

It has been discovered that titanium dioxide pigment coated with organo silane and incorporated in melt-fabricable fluoropolymer resin substrate provides an unexpected improvement in the contrast, and uniformity of contrast, of marks created in the substrate by the laser marking technique. While the mechanism for the improvement is not understood with certainty, the improvement in marking has accompanied the reduction in the level of TiO₂ agglomerates present in the fluoropolymer composition when melt fabricated. The reduction is evidenced both at agglomerate dimensions observable by optical microscopy at 70X magnification, at which scale agglomerates are substantially eliminated, and at agglomerate dimensions detectable only by electron microscopy. This effect of organo silane coating of TiO₂ on the pigmentation of fluoropolymers is surprising. If performance in this respect were a matter of compatibility between pigment and matrix, one would not expect the hydrocarbon character acquired by the TiO₂ pigment particle surface due to hydrocarbon organo groups of some silane coatings to provide any improved compatibility with a fluoropolymer over that of uncoated TiO₂.

Substrates suitable for marking by the improved laser marking method of this invention have matrices of melt-fabricable fluoropolymer resins. Fluoropolymers that can be used include those commonly used in applications for pigmented melt-fabricable polymers. Of particular interest are those fluoropolymers commonly used for extrusion of elongated shapes such as wire insulation, jacket for electrical or fiber optic cable, tubing, tape, and the like. Melt fabricable polymers useful in this invention include elastomeric polymers, but, obviously, elastomeric compounds will not include carbon black as a filler.

Fluoropolymers that can be used in the compositions of this invention are polymers of at least one fluorine-containing monomer, but may incorporate monomers containing no fluorine. The fluorinated monomers include those in the group consisting of fluoroolefins having 2-8 carbon atoms and fluorinated vinyl ethers (FVE) of the formula $CY_2=CYOR$ or $CY_2=CYOR'OR$ wherein Y is H or F, and -R, and -R'- are independently completely-fluorinated or partially-fluorinated linear or branched alkyl and alkylene groups containing 1-8 carbon atoms. Preferred -R groups contain 1-4 carbon atoms and are preferably perfluorinated. Preferred -R'- groups contain 2-4 carbon atoms and are preferably perfluorinated. Fluoropolymers used in this invention include but are not limited to the group of melt-fabricable copolymers of tetrafluoroethylene (TFE) with sufficient concentrations of at least one copolymerizable monomer to reduce the melting point significantly below that of PTFE. Such copolymers generally have melt viscosity in the range 0.5×10^3

to 60×10^3 Pa-s, but viscosities outside this range are known. Comonomers with TFE can include perfluoroolefins, FVE, and ethylene (E), for example, and these are preferred. Among perfluorinated comonomers, hexafluoropropylene (HFP) and perfluoro(alkyl vinyl ether), especially perfluoro(propyl vinyl ether) (PPVE), are most preferred. When the principal comonomer is E, minor amounts of a third monomer are commonly used to prevent high-temperature brittleness, with PPVE, perfluorobutyl ethylene (PFBE), and hexafluoroisobutylene (HFIB) being preferred. Other preferred fluoropolymers include chlorotrifluoroethylene (CTFE) polymers, including E/CTFE copolymers, and vinylidene fluoride (VF₂) polymers including homopolymers and VF₂ copolymers with one or more perfluoroolefins, particularly including HFP.

"Silanized" TiO₂ as used herein refers to TiO₂ pigment coated either with silane(s) or with a mixture of silane(s) and polysiloxane(s), also collectively referred to as organo silicon compounds.

TiO₂ pigment bases for the silanized TiO₂ useful in the present invention generally are in the rutile or anatase crystalline form. These are commonly made, respectively, either by a chloride process or by a sulfate process, though anatase may be subsequently calcined to the rutile form. In the chloride process, TiCl₄ is oxidized to TiO₂. In the sulfate process, titanium-containing ore is dissolved in sulfuric acid and the resulting solution goes through a series of steps to yield TiO₂. Both processes are described in greater detail in "The Pigment Handbook", Vol. 1, 2nd Ed., John Wiley & Sons, NY (1988). Certain finishing steps are commonly performed on the products of the foregoing processes, such as slurring if not already a slurry, filtering, washing, drying, and milling with a fluid energy mill. Fluid energy milling involves introducing dry TiO₂ pigment and a fluid, e.g., air or steam, into the outer portion of an inwardly spiraling vortex so as to convey the TiO₂ at high velocity against the housing of the spiral vortex to fracture aggregates, as described in U.S. Patent 4,427,451. Average TiO₂ particle size can be in the range 5-1000 nm, but is usually in the range 150-400 nm for effective performance as a white pigment. TiO₂ pigment bases used in this invention may contain other ingredients, usually but not always in the form of surface treatments. Additive substances include oxides such as alumina, silica, and tin oxide, as well as triethanolamine, trimethylolpropane, phosphates, fluorides, and the like. For use in the compositions of this invention, it is preferred if any such additives are of a ceramic type or other non-hydrated type to avoid potential release of water at processing temperatures of fluoropolymers.

Suitable silanes for use in the practice of this invention include silanes having the general formula




5 in which at least one R is a non-hydrolyzable organic group, such as alkyl, cycloalkyl, aryl, or aralkyl, having 1-20 carbon atoms, preferably 4-20 carbon atoms, most preferably 6-20 carbon atoms, and at least one R is a hydrolyzable group such as alkoxy, halogen, acetoxy, or hydroxy. The other two R are,
10 independently, hydrolyzable or non-hydrolyzable as above. It is preferred that at least two, and especially that three, of the R are hydrolyzable. The non-hydrolyzable R can be fluorine substituted. A silane having the foregoing description is herein called "organo silane" in reference to the non-hydrolyzable R group(s). Preferably, non-hydrolyzable R are non-functional. Alkyl,
15 cycloalkyl, aryl, and aralkyl are preferred non-hydrolyzable R, with alkyl being most preferred, including the possibility of any of these groups being fluorine substituted. When the hydrolyzable R are identical, the organo silane can be represented by



in which R' is non-hydrolyzable and R'' is hydrolyzable as defined above and $x = 1-3$. Preferred R'' include methoxy, ethoxy, chloro, and hydroxy. Ethoxy is especially preferred for ease of handling. Preferred silanes include
25 octyltriethoxysilane, nonyltriethoxysilane, decyltriethoxysilane, dodecyltriethoxysilane, tridecyltriethoxysilane, tetradecyltriethoxysilane, pentadecyltriethoxysilane, hexadecyltriethoxysilane, heptadecyltriethoxysilane and octadecyltriethoxysilane. Mixtures of organo silanes can be used.

The concentration of organo silane is typically from about 0.1 to
30 about 5 wt% based on total silanized pigmentary TiO_2 , and preferably about 0.5 to about 1.5 wt%

In an alternative embodiment, a mixture of organo silane with polysiloxane is useful in carrying out the invention. Suitable polysiloxanes are of the general formula



in which R may be organic or inorganic, $n = 0-3$, and $m \geq 2$. For example, polydimethylsiloxane (PMDS), vinyl phenylmethyl terminated dimethyl

siloxanes, divinylmethyl terminated polydimethyl siloxane, and the like are suitable polysiloxanes. PDMS is a preferred polysiloxane. Organo silane useful in the mixture may be the organo silane described above. Combined concentration of organo silane and polysiloxane, based on total silanized pigmentary TiO_2 , is from about 0.1 to about 5 wt%, preferably about 1-3 wt%. Especially preferred is about 0.5 to 1 wt% organo silane of formula (II) with R' being butyl or octyl, R'' being alkoxy, $x = 1$, and about 1 wt% PDMS. Desirably, the silane/polysiloxane ratio is in the range 1/2 to 2/1, and preferably is about 1/1.

Organo silanes and polysiloxanes are commercially available or can be prepared by processes known in the art. See, for example, S. Pawlenko, "Organosilicon Compounds", G. Thieme Verlag, New York (1980).

TiO_2 pigment may be treated with organo silane in a number of ways. Silane addition, for example, can be made neat or prehydrolyzed to a dry oxidation base, in a slurry, at a filtration step, during drying, at a sizing operation in a fluid energy mill (micronizer) or media mill, or in a blending step after grinding. For example, U.S. Patent 3,834,924 describes organosilane and pigment dispersion mixed or blended directly in a suitable solids mixing apparatus. An example of post-blending is described in U.S. Patents 3,916,735 and 4,141,751. Polysiloxane can be added in conjunction with silane or subsequent to silane addition. If water, either as liquid or vapor (steam) is present as a component of the process stream, hydrolysis of the hydrolyzable groups of the organo silane will occur and the silane coating will bond to the TiO_2 base. If the organo silane is added neat to the TiO_2 base, then moisture adsorbed on the TiO_2 will effect the hydrolysis. Hydrolysis of silanes is described in greater detail in "Organofunctional Silanes" by Union Carbide Corp. (1991). For preparation of the fluoropolymer compositions of this invention, it is most convenient if the hydrolysis of the hydrolyzable groups of the organo silane coating is done separately, and the silanized TiO_2 is ready for combination with fluoropolymer resin without need for attention to the coating process.

TiO_2 is frequently incorporated into polymeric materials for various purposes, including opacity, appearance, ultraviolet screening, identification, and so on. Fluoropolymers are among the polymeric materials in which TiO_2 is used, especially when the fluoropolymer is to be used as wire insulation or as cable jacket. The fluoropolymer compositions of this invention can have a wide range of silanized TiO_2 pigment concentration. If the concentration of TiO_2 is too low, effective pigmentation will not be achieved. If the concentration is too high, convenient processing and/or mechanical or

electrical properties may be adversely affected. Generally, TiO₂ concentration can be in the range of from about 0.1 wt% to about 70 wt% based on combined weight of TiO₂ and fluoropolymer. A TiO₂ concentration range of about 0.25-10 wt% is preferred in finished articles. When the purpose is simply to produce a white color, a concentration in the range of about 0.25-2 wt% is usually adequate. Preferred compositions for laser marking contain 1-10 wt% of silanized TiO₂ pigment, most preferably 1-5 wt%. If one is preparing a concentrate for subsequent dilution by unpigmented fluoropolymer resin to arrive at a lower concentration such as recited in the preceding sentences, then it is usually appropriate to select a high concentration such as 5-30 wt%, or a higher concentration ranging up to 50 wt% or even to about 70 wt%.

TiO₂ coated with organo silane can be incorporated into melt-fabricable fluoropolymer to form the fluoropolymer composition of this invention by any melt compounding technique known in the art. In forming or processing the compositions of this invention, it is believed that there is no reactive interaction between fluoropolymer and organic group of the organo silane. Generally, TiO₂ and fluoropolymer resin are brought together and then mixed in a blending operation that applies shear to the fluoropolymer melt. The fluoropolymer resin is usually available in the form of power, granules, pellets, or cubes. Commonly, TiO₂ and resin are first combined while the resin is in the solid state (not melted) and dry-blended in some way. This can be done in simple ways, such as by shaking in a bag or tumbling in a closed container, or in more sophisticated ways such as by using blenders having agitators or paddles. TiO₂ and fluoropolymer resin can be brought together by co-feeding the materials to an extruder and allowing the screw to mix them together before the resin reaches the molten state. The melt blending of TiO₂ and fluoropolymer resin can be done using known equipment, such as single-screw extruders, twin-screw extruders, internal mixers, and the like. Extruders are commonly used. The melt blending can be done as part of the process of forming a finished article of the composition, as by melt extrusion. Alternatively, the melt blending can be done in a preliminary step, optionally isolating the fluoropolymer composition, e.g., as cubes, followed by forming a finished article in a subsequent process. As one skilled in the art will recognize, there are many possible variations of the technique for preparing fluoropolymer compositions of the invention. One may, for example, first prepare a concentrate having high TiO₂ concentration, i.e., one composition of the invention, and then combine the concentrate with fluoropolymer resin containing no TiO₂ to obtain another composition of the invention.

TiO₂-pigmented fluoropolymer compositions frequently have no constituents other than fluoropolymer resin and pigment. However, the use of other additives is known. ETFE resins, for example, commonly contain very low concentrations of copper stabilizer. As a further illustration, fluoropolymers are sometimes crosslinked, e.g., by irradiation after fabrication to final shape, in which case it is known to use crosslinking promoters. The use of such other additives is within the scope of this invention.

The fluoropolymer compositions of this invention exhibit reduced populations of TiO₂ agglomerates in the melt-fabricable fluoropolymer resin matrix. These improvements are deduced from analysis of thin sections by optical and electron microscopy, and are attributed to use of TiO₂ having an organo silane coating.

Another benefit of organo silane coating on TiO₂ pigment is improved processibility of fluoropolymer compositions, especially fluoropolymer compositions having high pigment concentrations. For example, a composition containing 15 wt% silanized TiO₂ can be easily extruded with better surface quality than compositions having lower concentrations of TiO₂ without silane coating. Furthermore, compositions containing silanized TiO₂ pigment can be converted into finished articles, such as wire insulation, with higher yield than compositions containing TiO₂ pigment without silane coating.

TiO₂-pigmented fluoropolymers are commonly used in wire and cable constructions, either as wire insulation surrounding the electrical conductor or as jacketing for a cable having one or more insulated wires. Such fluoropolymers can also be used as jacketing for fiber optic cables. Insulated wire and jacketed cable wherein insulation and jacket, respectively, comprise the fluoropolymer composition of this invention are also within the scope of this invention.

The surface of shapes, e.g., wire insulation and cable jacket, fiber optic bundle jacket, etc., formed from the fluoropolymer composition of this invention exhibits improved response to laser marking techniques. The improvement is evidenced by an increase in contrast between mark and background, and in uniformity of contrast. An improved method of laser marking based on the fluoropolymer composition disclosed herein is part of this invention.

35

EXAMPLES

Polymer resins used in the preparing compositions for the examples and controls are identified in Table 1. Where melt flow rate (MFR) is mentioned, measurement method is specified in the ASTM standard given for the resin. Patent references are cited for general methods of preparation.

Table 1. Fluoropolymer Resins

<u>Code</u>	<u>Identification or Description</u>
FEP	Copolymer of TFE and about 8 mol% HFP, having MFR of about 7 and satisfying ASTM D-2116 Type I (U.S. Patent 2,946,763)
PFA	Copolymer of TFE and about 1.3 mol% PPVE, having MFR of about 15 and satisfying ASTM D-3307, Type I (U.S. Patent 3,528,954)
ETFE	Copolymer of E, TFE, and PFBE, having E/TFE ratio of about 0.9, about 1-2 mol% PFBE, and MFR of about 9, satisfying ASTM D-3159, Type II (U.S. Patent 3,624,250)
ECTFE	Copolymer of ethylene and CTFE, ASTM D-3275 Type III (Halar [®] grade 500, Ausimont)
PVDF	Believed to be copolymer of VF ₂ and HFP, or blend of VF ₂ homopolymer with VF ₂ /HFP copolymer (Kynar [®] grade 2800, Atochem)

5 Examples 1-10 illustrate various ways in which organo silane, or organo silane and polysiloxane, can be added to TiO₂.

Example 1

10 A TiO₂ pigment slurry in water, with 30-60 wt% solids and viscosity of 2200 cp, was treated with dilute NaOH to adjust pH to 9-11 and thereby reduce slurry viscosity to about 120 cp. The slurry was then processed through a 60-liter media mill at the rate of 3 gal/min (11.4 l/min) to achieve desired particle size reduction. At the discharge of the mill, the slurry was treated with 1 wt% octyltriethoxysilane (Union Carbide, now Osi) and spray dried to less than 1 wt% water.

Example 2

15 A TiO₂ pigment slurry, with 53 wt% solids and viscosity of 8500 cp, was treated with 0.2 ml of organic dispersant (amino methanol propane, 0.1

wt%) at room temperature and the slurry viscosity was thereby reduced to 20 cp. The slurry was then processed through a media mill as in Example 1. At the discharge of the mill, the slurry was treated with 0.8 wt% octyltriethoxysilane, stirred for 10 min at room temperature, and dried in an oven overnight to less
5 than 1 wt% water.

Example 3

3000 g of neutralized pigmentary TiO₂ were weighed into a pan and sprayed with 30 g of butyltrimethoxysilane (Union Carbide Corp.). The treated pigment was processed (micronized) in a fluid energy mill. The
10 micronized pigment was mixed in a Patterson-Kelley V-Blender with 30 g of polydimethylsiloxane (PDMS) (Huls Corp.).

Example 4

Example 3 was essentially repeated, except that
15 octyltriethoxysilane was used instead of butyltrimethoxysilane.

Example 5

Neutralized pigmentary rutile TiO₂ was treated with about 1 wt% each of octyltriethoxysilane and PDMS essentially as for Example 3, except that these compounds were added at the fluid energy mill through existing nozzles in
20 the grinding chamber.

Example 6

Pigmentary rutile TiO₂ was treated with about 1 wt% of octyltriethoxysilane by spraying, and processed through a fluid energy mill, essentially as for Example 3. PDMS was not present.

Example 7

Pigmentary rutile TiO₂ was treated with 1 wt% octadecyltriethoxysilane (Huls Corp.) by spraying.

Example 8

Example 7 was essentially repeated, except that
30 methytrimethoxysilane (Petrach) was used instead of octadecyltriethoxysilane.

Example 9

Example 6 was essentially repeated, except that hexyltrimethoxysilane (Petrach) was used instead of octyltriethoxysilane.

Example 10

35 Example 7 was essentially repeated, except that a solution in HFC-113 (1,1,2-trichloro-1,2,2-trifluoroethane) of a mixture of trichlorosilanes having fluorinated organo groups was used instead of octadecyltriethoxysilane. Such fluoroorgano silicon compounds are disclosed in U.S. Patent 3,450,738. The solution is commercially available (Zonyl[®] fluorosilane, DuPont Co.) In

this instance, the organo groups were alkyl of the formula $-\text{CH}_2\text{CH}_2\text{C}_n\text{F}_{2n+1}$ in which n was principally 8, 10 and 12. See U.S. Patent 5,276,194 for more detailed description of the fluoroalkyl mixture. The concentration of silane mixture in the solution was approximately 50 wt%. In this case, the solution
5 was sprayed on the TiO_2 and the HFC-113 was allowed to evaporate to deposit about 0.5 wt% of fluorosilane on the TiO_2 .

Examples 8-22 deal with the properties of fluoropolymer compositions containing TiO_2 , and with the state of TiO_2 in the fluoropolymer
10 compositions.

Example 11 and Controls

This example illustrates the benefit of silanized TiO_2 for laser marking a substrate containing TiO_2 pigment. ETFE resin as described above was compounded with about 2 wt% of rutile TiO_2 coated with
15 octyltriethoxysilane in accordance with any of Example 1, 2 or 6, and extruded onto AWG 20 stranded tin-plated copper conductor. AWG 20 stranded wire has diameter of about 0.037 inch (0.94 mm); diameter of the insulated wire was about 0.050 inch (1.3 mm). A similar insulated wire was prepared as Control A using a rutile TiO_2 that was not treated with silane. The wires were crosslinked
20 by electron beam irradiation.

Both wires were marked using five different Vektronics Model WV 1200 laser marking machines, and contrast between the mark and the unmarked insulation was measured. Average values over several marks for each test are summarized in Table 2. Control A is relatively good, exhibiting contrast
25 at the upper end of the prior art range. However, the marks on the wire insulation of this invention exhibit generally higher and more uniform contrast than the marks on the control. The raw data show that the higher contrast for the example of the invention has contributions both from higher reflectance of the background and lower reflectance of the marks, while the improvement in
30 uniformity is due to more uniform reflectance of the marks. Additionally, five samples of Example 11 wire were marked with a Capris Model 500 laser marking machine (Spectrum Technologies, Ltd.). Contrast values for the five samples were in the very narrow range 79-81%, with an average value of 80%. This result is also shown in Table 2 (Laser 6).

35 Pieces of insulation were removed from the Example 11 wire and Control B wire shown in Figure 6(b), sectioned, and examined by transmission electron microscopy (TEM). TEM micrographs taken at 11800X and 23000X magnification were analyzed using a Quantimet[®] Model 970 image analyzer and associated software (Cambridge Instruments) to determine TiO_2 particle

size and particle size distribution. The micrographs were scanned into the image analyzer using a high resolution video camera. Number average particle sizes yielded by the analyses were 216 nm for Example 8 and 280 nm for Control B, treating all particles as spherical equivalents of the observed shapes.

5 Particle size distributions were roughly log-normal in both instances, with distinctly higher populations of larger particles for Control B. Cumulative mass data provide more interesting information, and are summarized in Table 3. The first column gives some values of equivalent spherical diameter yielded by the analyses. The second and third columns, for Example 11 and Control B,

10 respectively, give the fraction of TiO_2 particle mass having equivalent spherical diameter greater than the value stated in the first column. The differences between the two sets of data are greatest in the range of diameters around 300-500 nm. For example, Control B had 65% of TiO_2 mass present in particles with diameter larger than 382 nm, but only 46% exceeded this diameter

15 for the example of the invention. Examination of 23000X micrographs revealed that many of the large particles for Example 11 and Control B were agglomerates, which image analysis treats as single particles. This comparison shows that the population of TiO_2 agglomerates having dimensions too small to observe under optical microscopy is reduced by organo silane coating of the

20 TiO_2 . Because of the extremely high TEM magnifications, this particular image analysis was not sensitive to exceptionally large agglomerates of the sort observed by optical microscopy in the controls for the following examples.

Table 2. Laser Marking Results

25

<u>Laser</u>	<u>Contrast (%)</u>	
	<u>Ex. 11</u>	<u>Contr. A</u>
1	76	73
2	77	75
3	71	66
4	71	72
5	69	62
6	80	--

Table 3. Cumulative TiO₂ Mass Data for Example 11 and Control

<u>Diam. (nm)</u>	<u>Mass Exceeding Diameter (%)</u>	
	<u>Example 11</u>	<u>Control B</u>
91	100	100
141	99	100
197	91	97
246	81	91
306	63	80
342	55	73
382	46	65
426	40	55
476	29	46
531	24	31
594	20	24
740	14	13

Examples 12-16 and Controls

5 For each of the polymer resins FEP, PFA, ECTFE, PVDF, and ETFE listed in Table 1, 10 lb (4.55 kg) of extrusion cubes were dry blended with 12.9 g of TiO₂ coated with octyltriethoxysilane by shaking cubes and silanized pigment together in a polyethylene bag to obtain a mixture that was 0.28 wt% white pigment. These are identified as Examples 12-16 in the order of

10 resin codes above. Controls C-G labeled in the same order were prepared in the same way and at the same concentration using pigmentary rutile TiO₂ having oxide surface treatment (Ti-Pure[®] titanium dioxide pigment grade R-960, DuPont Co.) as the white pigment. The pigment loading chosen was at the low end of the range for white pigmentation in order that opacity not interfere with

15 optical microscopy, below. Each of the blends was placed in the feed hopper of a 1.5-inch (38-mm) Davis Standard single screw extruder having length/diameter ratio of 24/1, and extruded through an in-line tubing die of about 0.75-inch (19-mm) diameter using melt temperatures appropriate to the individual resins. For Examples 12-13 and Controls C-D, the screw used had a mixing head

20 design. For Examples 14-16 and Controls E-G, the screw was a barrier screw with a mixing head section. Tubing was not formed; instead, molten resin was collected in a shapeless mass at the die exit and allowed to solidify.

Sections about 0.02 mm thick were sliced from the solidified pigmented masses using a cryogenic microtome (R. Jung AG) and examined

25 microscopically in transmitted light. Under 70X magnification, the examples

appeared uniform and generally free from pigment agglomerates, while the controls exhibit pigment agglomerates which are seen as large dark spots in one-chip video photomicrographs (at 70X magnification) presented as Figures 1-5 corresponding to Examples 12-16 and controls. Thus, the use of TiO₂ having a coating of organo silane resulted in melt-fabricable fluoropolymer compositions substantially free from TiO₂ agglomerates at a scale of examination that complements the electron microscopy discussed in Example 11.

10

Examples 17-21

The procedures of Examples 16 were essentially repeated, this time using five different silanized TiO₂ pigments in ETFE fluoropolymer resin and harvesting tubing exit the die. The silanized TiO₂ were prepared according to Table 4. Photomicrographs at 70X magnification, Figures 7-11, show a hierarchy of results. The octadecyl and hexyl silanes (Examples 18 and 20) appeared to yield results equivalent to Example 16. The fluoroalkyl silane (Example 21) yielded a few small agglomerates in this test. The mixed coating of butyl silane and PDMS (Example 17) yielded fewer but larger agglomerates. The methyl silane (Example 19) yielded a larger number of small agglomerates. A repeat of Control G yielded photomicrographs similar to Figure 5(a).

20

Table 4. Silanized TiO₂ for Examples 17-21

<u>Example</u>	<u>Silanized TiO₂</u>	<u>Figure</u>
17	Example 3	7
18	Example 7	8
19	Example 8	9
20	Example 9	10
21	Example 10	11

25

Example 22

The silanized and control TiO₂ pigments used in Examples 12-16 and Controls were dry-blended with melt-fabricable fluoropolymer extrusion pellets in various proportions to yield mixtures with pigment concentration in the range 5-30 wt%. The fluoropolymer was a TFE copolymer similar to that used in Example 12 but having MFR of about 22. Selected blends were extruded through a dual beading die with orifice diameters of 0.25 inch (6.4 mm) using a 1.5-inch (38-mm) Brabender Model 15-02 twin screw mixer, with a melt temperature of about 315°C at the die. The beadings were quenched in

30

water and chopped into pellets. Compositions containing the control pigment at concentrations of 10-30 wt% extruded poorly as judged by extrudate surface quality, exhibiting roughness including bumps. Only a composition with 5 wt% of control pigment extruded reasonably well by this standard, but extrudate still had surface bumps. A composition containing 15 wt% of silanized TiO₂ extruded well, exhibiting even better surface quality than the composition with 5 wt% of control pigment without organo silane coating.

Pellets containing 15 wt% of each pigment from the preceding experiments were dry-blended with resin containing no TiO₂ in a ratio of 3/97 to obtain blends containing 0.45 wt% pigment. These blends were then used to extrude white insulation onto AWG 24 solid copper conductor using a 60-mm Nokia Maillefer single screw extruder having length/diameter ratio of 30/1, equipped with a Maillefer 4/6 crosshead, a screw with mixing head, a 0.315-inch (8-mm) diameter die, and a 0.188-inch (4.8-mm) guider tip. Melt temperature was about 765°F (407°C). Line speed was 1500 ft/min (457 m/min) and drawdown ratio was about 100/1. The extrudate was air-cooled for about 45 ft (13.7 m), passed through a 2-ft (0.6-m) water bath, then travelled in air through a bead-chain spark tester operating at 2.5 kV to a takeup system. Resultant insulation thickness was 0.005-0.0055 inch (0.13-0.14 mm). Approximately 30,000 ft (9150 m) of wire insulated with each composition was produced. Additionally, a similar quantity of wire insulated with the natural fluoropolymer resin (no pigment) was produced. The insulation made from the composition containing silanized pigment had four faults at the spark tester, while faults were too numerous to count for the construction containing pigment without silane coating. The construction containing no pigment had one fault. These results show the benefit of fluoropolymer compositions containing silanized pigment in fabricating finished articles.

WHAT IS CLAIMED IS:

1. In the method of laser marking a substrate comprising melt-fabricable fluoropolymer resin and titanium dioxide pigment, the improvement comprising conducting said laser marking wherein said pigment is coated with a coating comprising organo silane.
2. In the method of Claim 1, wherein said substrate is cable jacket or electrical insulation.
3. The method of Claim 1, wherein said fluoropolymer is copolymer of tetrafluoroethylene and hexafluoropropylene, copolymer of tetrafluoroethylene and perfluoro(alkyl vinyl ether), copolymer of ethylene and tetrafluoroethylene, copolymer of ethylene and chlorotrifluoroethylene, polyvinylidene fluoride, or vinylidene fluoride copolymer.
4. A fluoropolymer composition comprising melt-fabricable fluoropolymer and about 0.1-70 wt% of titanium dioxide pigment coated with a coating comprising organo silane.
5. The fluoropolymer composition of Claim 4, wherein said organo silane is alkyl, cycloalkyl, aryl, or aralkyl silane.
6. The fluoropolymer composition of Claim 4, wherein said coating further comprises polysiloxane.
7. An insulated wire, wherein the insulation comprises the fluoropolymer composition of Claim 4.
8. A jacketed cable, wherein the jacket comprises the fluoropolymer composition of Claim 4.
9. In the process of melt extruding composition comprising fluoropolymer and titanium dioxide pigment, the improvement comprising conducting said extruding wherein said pigment is coated with a coating comprising organo silane.

FIG. 1a




FIG. 1b




FIG. 2a




FIG. 2b




FIG. 3a




FIG. 3b



FIG. 4a




FIG. 4b




FIG. 5a



FIG. 5b



FIG. 6a



FIG. 6b



FIG. 7




FIG. 8



FIG. 9




FIG. 10





FIG. 11



INTERNATIONAL SEARCH REPORT

International Application No. PCT/US 95/01941

A. CLASSIFICATION OF SUBJECT MATTER

H 01 B 7/36, C 08 L 27/12, C 08 K 9/06

According to International Patent Classification (IPC) or to both national classification and IPC⁶

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

H 01 B, C 08 L, C 08 K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JP, A, 04 309 548 (DAIKIN et al.) 02 November 1992 (02.11.92), paragraph 21, 27; examples.	4, 5
Y	& DATABASE WPIL, no. 92-412 075, -- DERWENT PUBLICATIONS LTD., London.	1-3, 7-9
Y	EP, A, 0 436 221 (FILOTEX) 10 July 1991 (10.07.91), column 1, line 32 - column 2, line 18. --	1-3, 7-9
A	EP, A, 0 329 884 (BRITISH AEROSPACE) 30 August 1989 (30.08.89), --	1, 4, 9

☒ Further documents are listed in the continuation of box C.☐ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search
04 May 1995Date of mailing of the international search report
06.06.95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

KUTZELNIGG e.h.

-2- INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 95/01941

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
	the whole document (cited in the application). -----	

ANHANG

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

ANNEX

to the International Search
Report to the International Patent
Application No.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/US 95/01941 SAE 106149

In diesem Anhang sind die Mitglieder
der Patentfamilien der in obenge-
nannten internationalen Recherchenbericht
angeführten Patentdokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visée ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

Im Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche	Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
JP A2 4309548	02-11-92	keine - none - rien	
EP A1 436221	10-07-91	FR A1 2656734 FR B1 2656734 US A 5111523	05-07-91 20-03-92 05-05-92
EP A1 329884	30-08-89	GB A0 8802683 GB A1 2215116 GB B2 2215116	02-03-88 13-09-89 29-07-92